

CEDRAL



The World of Roofs

FIBRE CEMENT SLATES

PROTECT YOUR ROOF AND WHAT'S UNDER IT



etex inspiring ways
of living



WHY CHOOSE CEDRAL SLATES FOR YOUR ROOF?

Our British Heritage

An integral part of homes across the UK for over a century, Cedral slates have deep-rooted history and heritage.

Formerly under the brand name of Eternit we are the UK's most experienced company when it comes to fibre cement slates and are proud to have been putting roofs over heads for decades.

As part of the global building materials group Elex, our residential range of products now unites worldwide under the Cedral brand, offering you more choice, more services and more expertise to make your build as easy as possible.

CONTENTS

12	THRU-TONE TEXTURED	14	CASE STUDIES	18	PROPERTIES & PERFORMANCE	20	SUPPORT & BACK-UP	22	SUSTAINABILITY & ENVIRONMENT
3	WHY CHOOSE CEDRAL SLATES FOR YOUR ROOF?	5	WHY CHOOSE FIBRE CEMENT?	6	RIVENDALE	8	BIRKDALE	10	THRU-TONE SMOOTH



Beautiful, affordable, sustainable

We want to offer one strong company for all construction and architectural needs. Cedral is our brand dedicated to the entire house and we are committed to driving the industry forward by developing beautiful, affordable and environmentally sustainable building products.

With local advisors across all corners of the UK as well as a dedicated internal customer service and technical advisory department, the Cedral team are on hand to guide you through every stage of your project.

WHY CHOOSE FIBRE CEMENT?

Fibre cement is a durable mineral material, lightweight and weather resistant. Composed of cement, cellulose, sand, synthetic fibres and water, it is incredibly strong, versatile and has many advantages.



Durable

Fibre cement is tough enough to withstand the most volatile weather conditions (frost, heavy rain, intense heat, light etc).



Fire resistant

Fibre cement has excellent fire behaviour (fire class A2-s1, d0 according to EN 13501-1:2018).



Sustainable

While fibre cement has been around for decades, innovations in technology ensure it contributes to eco-construction and respects the environment. A light-weight material, it considerably reduces the carbon footprint of any build.



Kerb appeal

Our slates come in a range of beautiful colours, textures and shapes and can be installed in many different ways, meaning you can choose to fit in or stand out.

YOUR HOME EXPRESSES WHO YOU ARE & WHAT YOU LIKE

Your personality is reflected in your interior but also in the exterior of your home. Your roof must also stand the test of time. Cedral fibre cement slates are an ideal material offering both beauty and performance. Our slates are the strongest on the market and offer maximum design scope, so whatever your roofing project, Cedral has got you covered.



RIVENDALE

FIBRE CEMENT SLATES

Cedral Rivendale slates are designed to reflect the qualities of natural slate. Available in Blue-Black, Cromleigh Graphite or Heather, Rivendale slates have a beautifully textured surface and dressed edges, combining the benefit of modern slate technology with the look of a natural slate. With more cement and fibres than any other, all Cedral slates are the strongest slates in the market.



✓ *Finely detailed surface*

✓ *Dressed edges*

✓ *Replicates natural slate*

The printing process restricts the total representation of colours. For true colour reference, please request product samples.

Technical data*

Size of slate	600mm x 300mm
Minimum pitch**	22.5° (100mm lap) 20° (110mm lap)
Moderate exposure	25° (100mm lap) 22.5° (110mm lap)
Severe exposure	90°
Maximum pitch	100, 110mm
Typical laps	Hook fixed 100 - 150mm
Slate hooks	245-250mm
Maximum gauge	4mm
Slate thickness	13.4 slatecm ² at 100mm lap 13.6 slatecm ² at 110mm lap 14.8 slatecm ² at 150mm lap
Covering capacity (net)	20.4 kg/m ² (0.20 kN/m ²) at 100mm lap 20.9 kg/m ² (0.20 kN/m ²) at 110mm lap 22.8kg/m ² (0.20 kN/m ²) at 150mm lap
Weight of slating (approx.)	4.00 lin/m ² at 100mm lap 4.08 lin/m ² at 110mm lap 4.45 lin/m ² at 150mm lap
Battens required (net)	50 x 25mm for rafters/supports not exceeding 600mm centres
Butten size recommended (fixed to BS 5534)	Slate nails (30 x 2.65mm) Copper disc rivets (19mm dia. x 2mm stem)
Fixings	14 gauge self sealing
Fixings screws	Length equal to lap
Slate hooks***	BS EN 492
Authority	

* Cedral fibre cement slates meet the strength requirement of BS EN 492, achieving an average bending movement greater than 50 N/100mm (Class B). The slates also have a minimum density of 1700kg/m³ and a normal modulus of 9mm

** The minimum recommended pitch and lap may be influenced by local circumstances, please contact the Technical Advisory Team for further information

*** When using slate hooks the perimeter/roofs areas (as defined by BS 5534) will require nails and rivets

† Please to order



Rivendale Blue-Black



Rivendale Cromleigh Graphite †

Sustainability

Green guide rating	A+ (Element ref: 812410008)
BES 6001	Very good – can achieve 3 credits
Credit uplift available with EPD	
Embodied carbon	Low carbon footprint of 16 CO ₂ g/m ²



BIRKDALE

FIBRE CEMENT SLATES

Cedral Birkdale slates combine a smooth surface with a dressed edge. Perfect in both wild spaces or urban places, this slate is perfect for both traditional and modern builds. We pack more cement and fibres into our slates ensuring they are the strongest and most durable for our customers.



Birkdale Blue-Black



Technical data*

Size of slate	600mm x 300mm
Minimum pitch**	22.5° (100mm lap) 20° (110mm lap)
Moderate exposure	25° (100mm lap) 22.5° (110mm lap)
Severe exposure	90°
Maximum pitch	100, 110mm
Typical laps	Hook fixed 100 - 150mm
Slate hooks	245-250mm
Maximum gudge	4mm
Slate thickness	13.4 slates/m² at 100mm lap 13.6 slates/m² at 110mm lap 14.8 slates/m² at 150mm lap
Covering capacity (net)	20.4 kg/m² (0.20 kN/m²) at 100mm lap 20.9 kg/m² (0.20 kN/m²) at 110mm lap 22.8kg/m² (0.20 kN/m²) at 150mm lap

Weight of slating (approx.)

Battens required (net)	4.00 lin/m/m² at 100mm lap 4.08 lin/m/m² at 110mm lap 4.45 lin/m/m² at 150mm lap
------------------------	--

Battens required (net)

Batten size recommended (fixed to BS 5534)	50 x 25mm for rafters/supports not exceeding 600mm centres
--	--

Fixings

Slate nails (30 x 2.65mm)	Copper disc rivets (19mm dia. x 2mm stem)
---------------------------	---

Fixings screws

14 gauge self sealing	Length equal to lap
-----------------------	---------------------

Slate hooks***

BS EN 492	
-----------	--

* Cedral fibre cement slates meet the strength requirement of BS EN 492, achieving an average bending moment greater than 30 kNm/m (Class B). The slates also have a minimum density of 1700kg/m³ and a nominal thickness of 10mm.

** The minimum recommended pitch and lap may be influenced by local circumstances, please contact the Technical Advisory Team for further information.

*** When using slate hooks, the perimeter of slates (as defined by BS 5534) will require nails and rivets.

Sustainability

Green guide rating	A+ (Element ref: 812410008)
BES 6001	Very good – can achieve 3 credits
Credit uplift available with EPD	
Embodied carbon	Low carbon footprint of 16 CO ₂ e/m²

The printing process restricts the exact representation of colours. For true colour reference, please request product samples.



✓ Smooth surface

✓ Dressed edges

✓ Traditional appearance

THRUTONE SMOOTH

FIBRE CEMENT SLATES

Cedral Thrutone Smooth slates have a superb smooth finish and square edges, which will result in a classic, elegant roof. Our fibre cement slates are unmatched in strength, giving you peace of mind when you choose Cedral for your roof.



✓ Smooth surface

✓ Square edges

✓ Clean, sharp lines

10 VISIT CEDRAL WORLD OR CALL 01283 501555 FOR MORE INFORMATION

Technical data*

Size of slate	600mm x 300mm	500mm x 250mm†
Minimum pitch**	22.5° (100mm lip)	22.5° (100mm lip)
Moderate exposure	20° (110mm lip)	
Severe exposure	25° (100mm lip)	25° (100mm lip)
	22.5° (110mm lip)	
Maximum pitch	90°	90°
Typical laps	100, 110mm	100mm
Slate hooks	Hook fixed 100-150mm	Hook fixed 100mm
Maximum gauge	245-250mm	200mm
Slate thickness	4mm	4mm
Covering capacity (net)	13.4 states/m² at 100mm lip 13.6 states/m² at 110mm lip 14.8 states/m² at 150mm lip	20.0 states/m² at 100mm lip
Weight of slating (approx.)	20.4 kg/m² (0.20 kN/m²) at 100mm lip 20.9 kg/m² (0.20 kN/m²) at 110mm lip 22.8 kg/m² (0.20 kN/m²) at 150mm lip	21.3 kg/m² (0.21 kN/m²) at 100mm lip
Buttens required (net)	4.00 lin/m/m² at 100mm lip 4.08 lin/m/m² at 110mm lip 4.45 lin/m/m² at 150mm lip	5.00 lin/m/m² at 100mm lip
Butten size recommended (fixed to BS 5534)	50 x 25mm for rafters/ supports not exceeding 600mm centres	50 x 25mm for rafters/ supports not exceeding 600mm centres
Fixings	Slate nails (30 x 2.65mm) Copper disc rivets (19mm dia. x 2mm stem)	Slate nails (30 x 2.65mm) Copper disc rivets (19mm dia. x 2mm stem)
Fixing screws	14 gauge self sealing	14 gauge self sealing
Slate hooks***	Length equal to lip	Length equal to lip
Authority	BS EN 492	BS EN 492

* Cedral fibre cement slates meet the strength requirement of BS EN 492, achieving an average bending movement greater than 50 N/90mm (Class B). The slates also have a minimum density of 1700kg/m³ and a normal thickness of 4mm.

** The minimum recommended pitch and lap may be influenced by special circumstances, please contact the Technical Advisory Team for further information.


*** When using slate hooks the perimeter/sical areas (as defined by BS 5539) will require nails and rivets.

† Made to order

Sustainability

Green guide rating	A+ (Element ref:812410008)
BES 6001	Very good – can achieve 3 credits
Credit uplift available with EPD	
Embodied carbon	Low carbon footprint of 16 CO₂e/m²

The printing process respects the exact representation of colours. For true colour reference, please request product samples.



Thrutone Smooth Blue-Black



Thrutone Smooth Terracotta†



Thrutone Smooth Turf Brown†



Thrutone Smooth Stone Green†



Thrutone Smooth Russet†




Thrutone Smooth Heather†

Other shapes



Bullnose†



Scalloped†



Channeled†



VISIT CEDRAL WORLD OR CALL 01283 501555 FOR MORE INFORMATION

THRUTONE TEXTURED FIBRE CEMENT SLATES

Cedral Thrutone Textured slates offer the same strength and durability as our flagship smooth slate, but have a subtle, textured finish which will enhance any roof and home.



Thrutone Textured Blue-Black



Thrutone Textured Terra-cotta[†]



Thrutone Textured Turf Brown[†]



Thrutone Textured Stone Green[†]



Thrutone Textured Russet[†]



Thrutone Textured Heather[†]



Technical data*

Size of slate	600mm x 300mm
Minimum pitch**	22.5° (100mm lap) 20° (110mm lap)
Moderate exposure	25° (100mm lap) 22.5° (110mm lap)
Severe exposure	90°
Maximum pitch	100, 110mm
Typical laps	Hook fixed 100 - 150mm
Slate hooks	245-250mm
Maximum gudge	4mm
Slate thickness	13.4 slates/m² at 100mm lap 13.6 slates/m² at 110mm lap 14.8 slates/m² at 150mm lap
Covering capacity (net)	20.4 kg/m² (0.20 kN/m²) at 100mm lap 20.9 kg/m² (0.20 kN/m²) at 110mm lap 22.8kg/m² (0.20 kN/m²) at 150mm lap

Battens required (net)

4.00 lin/m/m² at 100mm lap
4.08 lin/m/m² at 110mm lap
4.45 lin/m/m² at 150mm lap

Batten size recommended (fixed to BS 5534)	50 x 25mm for rafters/supports not exceeding 600mm centres
--	--

Fittings	Slate nails (30 x 2.65mm) Copper disc rivets (19mm dia. x 2mm stem)
----------	--

Fittings screws	14 gauge self sealing
Slate hooks***	Length equal to lap

Authority

- * Cedral fibre cement slates meet the strength requirement of BS EN 492, achieving an average bending moment greater than 50 kN/m² (Class B). The slates also have a minimum density of 1700kg/m³ and a normal thickness of 4mm.
- ** The minimum recommended pitch and lap may be influenced by local circumstances, please contact the Technical Advisory Team for further information.
- *** When using slate hooks the permeable local areas (as defined by BS 5534) will require nails and rivets † Made to order

Sustainability

Green guide rating	A+ (Element ref 812410008)
BES 6001	Very good – can achieve 3 credits
Credit uplift available with EPD	
Embodied carbon	Low carbon footprint of 16 CO ₂ e/m²

The printing process reflects the exact representation of colours. For true colour reference, please request product samples.



✓ Detailed surface


✓ Square edges

✓ Resembles natural slate

CASE STUDIES



Birkdale Blue-Black, Holcombe Moor Training Camp



Rivendale Blue-Black, Ronald McDonald House

CASE STUDIES



Thurstone Textured Blue-Black, Mount Wise



Birkdale Blue-Black, Cedar Court



Thurstone Blue-Black, Edith Cavell Hospital



Thurstone Smooth Blue-Black, Social Housing Development

PROPERTIES & PERFORMANCE

Features of Cedral fibre cement slates

- Can achieve an A+ rating in the BRE Green Guide
- Low carbon footprint of 16 CO₂ e/m²
- BES 6001 certified 'Very Good'
- Proven in application to last in excess of 60 years
- Clean, low energy production process
- Fully recyclable

Recyclability

At end of life crushed fibre cement products can be recycled without need for further processing as a raw material for use in Portland clinker.

Environmental Product Declarations

An Environmental Product Declaration has been issued for Cedral fibre cement slates and is available on cedral.world

Declarations of performance

Declarations of performance for all Cedral slates are available on cedral.world.

Composition and manufacture

Cedral fibre cement slates are manufactured from cement, water, selected cellulose and polymeric fibres, sheet formers and fillers which are all bonded together using the Hatschek rotational cylinder process. Slates are cut from formed base sheets, pressed and cured and in a separate process cured slates are sealed on the reverse, sprayed with an acrylic coating, cooled and stacked.

Density and thickness

Cedral Fibre Cement Slates have an average density of 1970kg/m³ (minimum of 1750kg/m³) when tested to BS EN492 and a nominal thickness of 4mm.

Performance

The slates are tested for resistance to wind driven rain and meet the requirements of BS 5534 'Code of practice for slating and tiling (including shingles)' with respect to windloading, when fixed in accordance with our recommendations.

Strength and durability

Cedral fibre cement slates meet the strength requirements of BS EN 492, achieving an average bending moment greater than 50Nm/m (Class B).

Fire resistance

Fibre cement has excellent fire behaviour (fire class A2-s1, d0 according to EN 13501-1:2018).

Cedral fibre cement slates are non-combustible and considered 'deemed to satisfy' without the need for further testing in relation to the requirements for external fire performance when tested for fire protection and spread of flame to BS EN 1187 Test methods for external fire exposure to roofs (BS 476-3).

There are no restrictions on their use under the Building Regulations and they achieve a Class 0 surface spread of flame when tested to BS 476-7 and are classified Class O A roof incorporating the slates is designated AA as referred to in Table A5 of Notional designations of roof coverings.

Fixing specification

Slates should be fixed in accordance with the recommendations of BS 5534. The Technical Advisory Service can provide a fixing specification, given the relevant criteria relating to type of slate, site location, topography, and building/roof dimensions.

Consideration should be given to sealing any cut edges to prevent potential efflorescence showing. Please contact the Technical Advisory team for more details at techadv@cegroup.co.uk

Environmental effects

Thermal

The thermal resistance (R) of Cedral fibre cement slates when dry is 0.011 m²K/W.

For the purpose of thermal transmittance calculations, the 'R' values above should be substituted by a figure of 0.12m²K/W which indicates the roof covering and airspace behind the slates. An 'R' value of 0.002m²K/W should be added for the roof underlay.

Heat

After an initial period of stabilisation slates are normally unaffected by the range of climatic temperatures (-20°C to +70°C). Slates should be laid with a maximum gap of 5mm to accommodate any movement induced by changes in temperature and to facilitate the fitting of the full roof.

Frost

Unaffected by frost and meets the requirements of BS EN 492.


Sunlight

The acrylic coating used on the slate surface has good colour stability proven over long periods of exposure to UV and sunlight. Some lightening may occur over a period of exposure to sunlight and normal weathering, which may affect the surface coating. This gradual lightening is similar to that experienced with natural slate.

Atmospheric pollution

Suitable for most rural, marine and normal industrial environments. Avoid discharging of gases or liquids from chemical processes onto the surface of the slates.

Anatomy of a Cedral fibre cement slate



Resistant to all but the most highly polluted atmospheres where sulphur dioxide levels exceed 70 microgrammes/m³ of air.

For advice on the suitability of application, please contact the Technical Advisory Team.

Electricity

Cedral fibre cement slates are electronically insulating. Reference should be made to BS 6651 for recommendations on the protection of buildings against lightning strikes.

Biological effects

Birds and rodents

Not affected or degraded by birds, rodents or insects.

Mosses and lichens

Water absorption of the slates is around 18%. The growth of mosses and lichens may occur over time, but does not adversely affect their performance. The acrylic coating helps to inhibit organic growth on the surface for a period of 5 to 15 years. Removal may only be required if they affect the drainage of water from the roof.

Health and Safety Guidance Sheets

Cedral fibre cement slates can be simply scored and snapped with no dust creation, or cut with standard hand tools without requiring compliance with Health and Safety Guidance Sheet 5 (August 2012). If cutting slates with machine tools, measures to reduce the effect of dust should be taken in accordance with the HSE Guidance Note EH 40 'Occupational Exposure Limits' and EH 44 'Dust in the workplace: general principles of protection'.

SUPPORT & BACKUP

At Cedral, we are committed to providing outstanding customer care. Whether you are embarking on your own self-build or renovation project, or are an architect, roofing installer or housing developer, we are there to support your project at every stage.

From inspiration to information, Cedral roofs have got you covered.



Customer Service & Sales

We have a team of highly experienced local advisors covering every corner of the UK who are available to discuss your roofing requirements, as well as a dedicated internal customer service team who are always on hand to support you.

Email: info@cedral.co.uk

Tel: +44 (0) 1283 501 555

To find your nearest stockist, please visit www.cedral.world

Technical Support

Specifiers and installers require prompt, knowledgeable and detailed responses to a vast range of enquiries covering everything from the embodied energy of a typical roof state, to the different ventilation options available, as well as installation advice and guidance.

Our Technical Advisory Team is staffed by a qualified team with specialist knowledge not only of all Cedral roofing products, but also crucially, of how those systems integrate with other roofing components and comply with Building Regulations, Health and Safety, environmental and other critical roofing criteria.

For all technical queries, please contact us at:

Email: techuk@cedral.co.uk

Tel: +44 (0) 1283 501 505

RAISING THE STANDARDS OF ROOFING

EAVES

Are the eaves constructed properly?

BATTEN GAUGE

Are the battens set to the gauge properly?

UNDERLAY

Is the underlay laid correctly?

FIXINGS

Are the fixing products installed correctly?

VENTILATION

Does the roof ventilation comply with the building regulations?

AT CEDRAL ROOFS, WE HAVE A SIMPLE 10-POINT CHECKLIST TO ENSURE A PERFECT ROOF

THE RIDGE

Is the ridge fixed in accordance with Cedral's recommendations?

THE HIP

Is the hip fixed in accordance with Cedral's recommendations?

PITCHED METAL VALLEY

Is the valley constructed correctly with valley boards set at correct level?

THE VERGE

Is the verge correctly detailed?

SLATES

Have the slates been laid correctly?

You can also download our fixing guide on cedral.world for more detailed guidance on installation of our Cedral fibre cement slates.

SUSTAINABILITY & ENVIRONMENT

At Cedral, we are dedicated to building more beautiful worlds and take every measure to ensure our products are sustainable and respectful to the environment.

As part of the Etex group, we have been at the forefront of sustainability in our industry for a very long time and are committed to reducing the environmental and

social impacts of our operations. We foster a strong environmental awareness among our workforce and invest in a range of resources to achieve tangible environmental progress through our ongoing environmental improvement programme, as part of the ISO 14001 standard. We are also fully committed to the maintenance of a healthy and safe environment for our employees, for our customers and the local communities in which we operate through our ongoing certification to the OHSAS 18001 safety management system. Annual audits provide third-party assessment and verification of our efforts to manage our environment and social impacts.



At Cedral
we build more
beautiful worlds



BES 6001 'Very good'

Demonstrating our commitment to sustainable building, all our roofing products are certified 'Very Good' under the BES 6001 standard for responsible sourcing and therefore contribute to extra credits under BREEM and The Code for Sustainable Homes.

Adoption of the BES 6001 Framework Standard for Responsible Sourcing enables us to take a more responsible and sustainable approach to the sourcing of the materials that go into making our products. The BRE standard, BES 6001, has been published to enable construction product manufacturers, like Etex, to ensure and then prove that their products have been made with constituent materials that have been responsibly sourced. Cement suppliers are chosen for their proximity to factories in order to minimise transport distances. Wood cellulose for fibre cement production is sourced from eco-certified plantations (FSC & PEFC). Timber used in our pallets are sourced from FSC managed forests, and wherever possible, recyclable cardboard and plastics are used for banding, interleaves, bags and boxes.



Embodied carbon

Embodied carbon figures are available at product level for our entire roofing range. This absolute clarity of environmental information allows our customers to make informed choices.



BREEM and the Code for Sustainable Homes

Credits gained from specifying our A-rated products, combined with additional credits from BES 6001 make our products more beneficial to the specifier.



Quality standard

All Cedral's factories are ISO 9001, 14001 and ISO OHSAS 18001 accredited. They achieve the highest standards in quality, health and safety and the environment.



CE Marking

All of our products covered by an EN Standard carry an appropriate CE Mark. This means that our products meet the required safety standards and have a guaranteed level of quality.



more at cedral.world

Tel +44 (0) 1283 501555 Email infouk@etexgroup.com
Etex (Exteriors) UK, Wellington Road, Burton-upon-Trent, Staffordshire DE14 2AP

June 2020

